

PPF Metallic Silver

General

It is a phthalate free and PVC free printing base used to achieve colored printing effect with elastic, metallic silver covering and soft touching properties in textile printing.

Advantages

- PPF Metallic Silver gives metallic silver effect to printings. It is doesn't contain phthalate and PVC. Suitable to ecological standards.
- It is ready to use Metallic Base.
- It is available in Silver.

Applications

- PPF Metallic Silver is applied to the surface desired to be made in print.
- Its curing time is at 320°F / 160°C; 1,5 mins.

Usage

- PPF Metallic Silver is used to metallic silver effect. It is advised to print with the silk-screen that are made between 43-120 mesh.
- 60-80 Shore, V type dr. blade should be used. After using, the silk-screen should be cleaned with synthetic thinner.

Storage & Shelf Life

- Keep containers dry and tightly closed. Store in a ventilated place between (+5)-(+30)°C /(+41)-(+86)°F of temperature.
- It should be consumed within 2 years after the production date.

Important

The technical application and information that have been given above, are designed only as using instructions. Should not be considered as a warranty for any other use. When any help or assistance is required, our technical department is ready for help.

In case of emergency, Safety Data Sheet of this product should be ready for help at the working area. The warnings are given on safety data sheet of this product is for use outside the manufacturer/ distributor to direct/indirect can not be held responsible for any loss or damage.



TECHNICAL DATA SHEET

Technical Details



Appearance
Paste



Odor
Characteristic



Color
Metallic - Silver



Viscosity
[(77 °F) sp: 93, rpm: 2 Brookfield] :
300.000 – 400.000 [mPa.s]



Density
1,083 g/cm³ (77°F)



pH
N/A



Boiling Point
>100°C (212°F)



Solubility
N/A



Explosion Hazard
It is not explosive



Packaging Information
PPF Metallic Silver is packed in
10/20/25 kg plastic cans.